

Warmteweerstand - MOSO® Bamboe Vloeren

PRODUCT	TYPE	Warmteweerstand m ² ·K/W (R-waarde)	Thermische geleidbaarheid W/mK
Bamboo Elite	SIDE Pressed / Plain Pressed DENSITY	0,0882 0,0696	0,1700 0,1868
Bamboo Elite Premium	SIDE Pressed / Plain Pressed DENSITY	0,0882 0,0725	0,1700 0,2068
Bamboo Excellence	SIDE Pressed / Plain Pressed DENSITY	0,1152 0,1091	0,1302 0,1375
Bamboo Ultradensity 18 mm	DENSITY	0,0645	0,2793
Bamboo Ultradensity 20 mm	DENSITY	0,0716	0,2793
Bamboo Supreme	SIDE Pressed / Plain Pressed DENSITY	0,0588 0,0471	0,1700 0,2125
Bamboo INDUSTRIALE	SIDE Pressed DENSITY	0,0588 0,0392	0,1700 0,2550
Purebamboo	SIDE Pressed / Plain Pressed DENSITY	0,0882 0,0471	0,1700 0,2550
Topbamboo	SIDE Pressed / Plain Pressed DENSITY	0,0591 0,0542	0,1693 0,1846

NB Of een product in combinatie met vloerverwarming kan worden gebruikt hangt van diverse factoren af. **DolOpHout** adviseert je graag!

Bron: www.moso-bamboo.com